



(19)

PCT/CA 2004/001431

BZ

(11) Publication number: 200

Generated Document.

PATENT ABSTRACTS OF JAPAN

(21) Application number: 11242421

(51) Intl. Cl.: G02F 1/1337 G03F 7/038

(22) Application date: 30.08.99

(30) Priority:	(71) Applicant: HAYASHI TELEMPU C
(43) Date of application publication: 16.03.01	(72) Inventor: SAKAI TAKEYA UETSUKI MASAO KAWATSUKI YOSHIO
(84) Designated contracting states:	(74) Representative:

(54) LIQUID CRYSTAL ALIGNMENT LAYER, ITS MANUFACTURE AND LIQUID CRYSTAL DISPLAY DEVICE**(57) Abstract:**




PROBLEM TO BE SOLVED: To obtain a liquid crystal alignment layer effective in a liquid crystal display device without elongating time for a aligning treatment by manufacturing the liquid crystal alignment layer in a stage for applying a polymer having a specified structure on a substrate and in a stage including an operation for photo-irradiating the applied polymer.

SOLUTION: The solution of a polymer 14 having a structure expressed by the formula I, II or the like is applied on a substrate 15. The polymer (resin film) 14 applied on the substrate 15 is irradiated through an optical device 13 (e.g. a Glan-tailor prism) with a polarized UV 17 generated by converting a non-

BEST AVAILABLE COPY

polarized light 16 generated from a UV lamp 11 excited by a power source 12 to form a liquid crystal alignment layer. The (-R1)-(-R5) in the formula I and II each denotes a -H, halogen group or alkyloxy group such as a methoxyl group. And (-R6)-(R9) each denotes -H, -CN, a phenyl group, a phenoxy group, an alkyl group such as a methyl group or an alkyloxy group such as a methoxyl group.

COPYRIGHT: (C)2001,JPO



BEST AVAILABLE COPY